



GATOR WRAP

Infi-Shield® External Gator Wrap



Infi-Shield® Gator Wrap prevents infiltration by providing a water-tight seal around any manhole, catch basin or concrete pipe joint. Gator Wrap resists harsh soil conditions and also provides a root barrier for any crack or joint. Infi-Shield® Gator Wrap installs easily with no special tools and can be immediately backfilled.

EPDM Rubber Specifications

Physical Properties	ASTM Test Method	Typical Value
Sheer Strength	D816	15 lb. PSI min
Tensile, PSI	D412	50 PSI
Elongation %	D412	500 %
Penetration	D217	40/120 MM
Low Temperature	D746	Minus 49° F flexibility
Heat Aging	D573 7 days @ 90 degrees C	
Tensile Strength	minimum, PSI (MPa) > 100 PSI	Pass
Fusion	5/64" (0.2) max	Pass
Elongation %	minimum 300% at break	Pass
Ozone Resistance	no visible signs of cracking	Pass
Aging and Storage	300% elongation applied (10 Years)	Pass
UV Resistance	No visible signs of cracking	Pass

Infi-Shield® Gator Wrap Specification

Each manhole, catch basin or pipe joint shall be sealed with an external rubber sleeve similar to the Infi-Shield Gator Wrap as manufactured by Sealing Systems Inc (763-478-2057). The seal shall be made of a Stretchable, Self-Shrinking, Intra-Curing Halogenated based rubber with a minimum thickness of 30 mils. The back side of each unit shall be coated with a cross-linked re-enforced butyl adhesive. The butyl adhesive shall be non-hardening sealant with a minimum thickness of 30 mils. The seal shall be designed to stretch around the joint and then overlapped creating a cross-link and fused bond between the rubber and butyl adhesive. Gator Wrap forms a continuous rubber seal on a manhole joint which prevents water and soil from infiltrating through the manhole, catch basin or concrete pipe joint.

INFI-SHIELD GatorWrap® is available in 6" and 9" widths and comes in a 50 foot roll or in a user-friendly kit which has six sixteen foot rolls. Upon special order, we can also manufacture a 12" width but please allow four weeks for delivery.

Material meets ASTM C923 and C877 – Mastic Meet ASTM C990.
Disclaimer: This technical data information and recommendations offered are based on test results, and findings we believe to be reliable and complete.



Sealing Systems, Inc.

9350 County Road 19 ♦ Loretto, MN 55357 ♦ 763-478-2057 ♦ 800-478-2054 ♦ Fax 763-478-8868 ♦ www.infi-shield.com



GATOR WRAP

INSTALLATION INSTRUCTIONS



1. Expose the area that is to be sealed. Clean the entire area around the joint with a wire brush and whisk broom. Remove any sharp protruding edges around the joint with an abrasive tool. When finished cleaning, the entire area must be dry and free of any dirt.



2. Remove the first foot of paper backing from the mastic. Center and place the Gator Wrap around the joint. Continue to remove paper backing as you apply the Gator Wrap to the entire structure.



3. Seal the overlapping area with a 6" overlap. Be sure not to stretch material at the overlap area.



4. Cut excess material using a utility knife. Using a rubber mallet or hand held roller, firmly flatten the Gator Wrap 360 degrees around joint.

Material: Rubber meets ASTM C923 and C877 – Mastic Meet ASTM C990

Disclaimer: This technical data information and recommendations offered are based on test result, and findings we believe to be reliable and complete.



Sealing Systems, Inc.

9350 County Road 19 ♦ Loretto, MN 55357 ♦ 763-478-2057 ♦ 800-478-2054 ♦ Fax 763-478-8868 ♦ www.infi-shield.com